

QuantumUHPC, with or without fibre, is a superior-grade concrete material known for its combination of high strength, high durability, excellent crack control, and perfect flowability. It is formulated using cementitious materials, sand/aggregates and advanced admixtures to achieve unparalleled performance in various construction applications.

#### **APPLICATIONS**

**QuantumUHPC** is appropriate for a broad spectrum of structural applications, especially where superior mechanical behaviour and improved durability are needed. Some applications are (but not limited to):

- High-rise buildings
- Bridge decks and overlays
- Marine structures
- Precast elements
- Industrial flooring
- Architectural facades
- Infrastructure rehabilitation

#### WHITE

**QuantumUHPC White** is the basis for any color. Any pigment can be added to achieve the expected color

## **CO2 REDUCTION**

81 kg/m<sup>3</sup>

# PRIMARY ENERGY REDUCTION

376 MJ/m<sup>3</sup>

### **REDUCE MATERIAL**

**Up 30%** 

#### QUALITY

Increased

#### POROSITY

Decreased

#### WORCABILITY

Stabilized

# COMPRESSIVE STRENGTH

150 MPa

## FLEXURAL STRENGTH

25 MPa

#### COLORE

White



#### **COMPOSITIONS and MATERIALS**

**QuantumUHPC** is composed of high-quality raw materials, including cementitious materials, sand/aggregates, and admixtures, all pre-mixed for convenience. On the construction site, only water needs to be added. **QuantumUHPC** can be delivered with or without fibres.

#### **TECHNICAL PARAMETERS**

- compressive strength: up to 230 MPa with fibers
- compressive strength: 180MPa (28d) with high energy mixer
- compressive strength: 120MPa 150MPa (28d) with simple compulsory mixer or planetary mixer
- flexural strength (matrix): up to 19 MPa with high energy mixer
- flexural strength (reinforced) up to 75 MPa
- fracture energy 50 90 kN/m
- possible unit thickness > 5 mm
- carbonating 1.5 mm after 3 years
- chloride-diffusion: no capillary pores, not measurable with standard methods
- water resistance: no capillary pores, not measurable with standard methods
- frost-resistance < 100 g/m2</li>
- shrinkage 1 1.5 ‰
- crack width << 0.1 mm</li>
- density 2.300 kg/m3

**QuantumFusion** — your technology partner for working with white UHPC

At **QuantumFusion**, we understand that working with UHPC is more than just purchasing a material — it's a complete process where every detail matters. That's why we offer not only high-quality white UHPC mix, but also full technical support.

Our team helps set up production, adapt the mix design to your specific needs, train your staff, and ensure consistent quality at every stage. We're with you from the first batch to full-scale production — so you get not just a product, but confidence in the result.

QuantumFusion — UHPC with intelligence, experience, and support.

QuantumFusion GmbH 34513 Waldeck Germany www.quantumfusion.de contact@quantumfusion.de



SOLVING CONCRETE CHALLENGES,
BUILDING
BETTER FUTURE